

Ningbo Asia Pulp & Paper

NINGBO FOLD

C1S Ivory

Basis Weight		Thickness		Stiffness (Taber 15°)	
g/m ²	24"x36"	µm (±4%)	pt (±4%)	mN·m (±10%)	
±3%	500 (lb)			CD	MD
190	117	245	9.6	1.7	2.9
210	129	275	10.8	2.3	3.9
230	141	310	12.2	3.2	7.2
250	154	340	13.4	4.1	7.7
270	166	370	14.6	5.1	8.3
300	184	415	16.3	7.1	13.2
325	200	460	18.1	9.3	16.5
350	215	490	19.3	11.0	20.4
400	246	555	21.9	15.4	25.3
440	270	610	24.0	19.8	35.2

Property	Unit	Value
PPS (Top)	µm	≤1.8
Moisture	%	6.0 ±1.5
Brightness (Top)	%	90 ±2
75°Gloss(Top)	%	50 ±5
IGT Blister(Top)	m/s	≥1.0
COBB Test(60s) (Top)	g/m ²	40±15
PLY Bonding	J/m ²	≥130

Test condition (ISO): temp 23±1°C, relative humidity 50±2%

Note: Shaded substances are non-regular substances which are not produced regularly.