

NINGBO POKER

Playing Card Board(blue center)

| Basis Weight | | Thickness | | Stiffness (Taber 15°) | |
|------------------|---------------------|-----------|-----------|-----------------------|-----|
| g/m ² | 24"x36" 500 (lb) | μm (±12) | pt (±0.5) | mN·m (±10%) | |
| | | | | CD | MD |
| 270 | 166 | 270 | 10.6 | 3.0 | 5.1 |

| Property | Unit | Value |
|---------------------------|------------------|----------|
| PPS (Top/Back) | μm | ≤2.2/2.7 |
| Moisture | % | 7.0±1.5 |
| Brightness (Top/Back) | % | 85±2 |
| 75°Gloss(Top/Back) | % | 50±5 |
| IGT Blister(Top/Back) | m/s | ≥1.0 |
| COBB Test(60s) (Top/Back) | g/m ² | 40±15 |
| PLY Bonding | J/m ² | ≥130 |

Test condition (ISO): temp 23±1°C, relative humidity 50±2%

Note: Shaded substances are non-regular substances which are not produced regularly.