

ZENITH

C1S Ivory Hi Bulk (GC1 Hi Bulk)

Basis Weight		Thickness		Stiffness (Taber 15°)	
g/m ² ±3%	24"x36" 500 (lb)	µm (±4%)	pt (±4%)	mN·m (+0/-20%)	
				CD	MD
215	132	305	12.0	4.4	8.8
235	144	355	14.0	5.5	11.0
250	154	380	15.0	7.5	14.3
270	166	410	16.1	9.0	17.6
295	181	460	18.1	12.1	24.8
325	200	510	20.1	16.1	31.4
350	215	560	22.0	18.7	38.5

Property	Unit	Value
PPS (Top)	µm	1.4±0.3
Moisture	%	6.0 ±1.0
Brightness (Top)	%	91.5±2
75°Gloss(Top)	%	50±5
IGT Blister(Top)	m/s	≥1.5
COBB Test(60s) (Top)	g/m ²	40±15
PLY Bonding	J/m ²	≥130

Test condition (ISO): temp 23±1°C, relative humidity 50±2%

Note: Shaded substances are non-regular substances which are not produced regularly.